

PRODUCT DATA SHEET

Product #40940


Silica Gel, Technical Grade, 60A, 63-200um

Silica quality is achieved using a controlled manufacturing process, from highly pure raw materials to tightly monitored production methods. A large, automated batch scale process (180kg) is used to produce Sorbtech Technical Grade, providing high quality reproducible chromatographic separations with uniformity between batches.

The efficiency of liquid chromatography relies on narrow particle size distributions (typically >90% in range), very high mechanical stability, and a high specific surface area to deliver consistent and reliable results. This irregularly shaped porous silica is specifically created to use in liquid chromatography as column packing material for general purification of natural products, food, cosmetics, pharmaceutical, and nutraceutical ingredients.

Reliable silica for your research

Sorbtech Technical Grade is a proven, highly successful packing material that provides fast, effective, and reproducible separations. Sorbtech Technical Grade is available in multi-ton quantities with a wide variety of package sizes to meet individual applications and economic requirements.



Test Criterion	Unit	Specification
Under size, air jet sieve Alpine 63 μm	% w/w	≤ 10.0
Over size, air jet sieve Alpine 200 μm	% w/w	≤ 10.0
Residual water, 160°C, 15 min	% w/w	≥ 7.0
pH-value, suspension 5% w/w, ISO 787-9	рН	6.0 - 8.0
Tapped bulk density ISO 787-11	g/L	400 - 600
Pore volume, N ₂ isotherm	mL/g	0.65 - 0.90
Surface specific, N ₂ isotherm, sBET	m²/g	450 - 550
Pore size calculated, N ₂ isotherm	Å	47 - 80

Storage Store silicas in original, sealed packaging. Seal tightly after each use.

Packaging Size 500g, 1kg, 2.5kg, 5kg, 25kg

CAS-Nr. 7631-86-9

EINECS-Nr. 231-545-4

REACH-Nr. 01-2119379499-16-0036

The information contained in this data sheet is believed to be a true and accurate representation of average properties obtained from current production and should not be considered guaranteed specifiations. Any recommendations or suggestions are made without warranty or guarantee, since the conditions of use are beyond our control. Nothing contained herein shall be construed to imply permission, inducement, or recommendation to practice any invention or patent owned by others without authorization from the owner of the patent.